

CONCRETE PROOF Water-Proofing and Plasticizing Concrete Admixture

Description

A liquid concrete admixture to concrete and mortars that allows for an increased workability; improves flowing of concrete, mortars including self leveling mortars, and rendering materials. In addition, it also acts as a water-proofing agent.

Object

CONCRETE PROOF is recommended for use for water-proofing of masonry and concrete structures as also to facilitate the placing of concrete on objects such as:

- Dams and reservoirs
- Canals, tunnels and culverts
- Sewerage, waste water and waste water treatment plants
- Swimming pools, water-tanks
- For the placing of self leveling mortars where high tolerances are required

Advantage

- Improves workability of all concrete, mortar and rendering mixes
- Provides for an easier compaction of concrete, thereby improving density of concrete which in turn reduces water permeability and improves waterproofing characteristics
- Increases compressive and flexural strength of concrete and mortars
- Chloride-free and thus not

aggressive towards reinforcement steel
Improves flow-characteristics of concrete thereby providing for faster pumping with less wear and tear on mechanical parts in concrete pumps and thus reducing the cost of placement of concrete

Standard

Meet -ASTM C-494 Type A.

Instruction for Use

is supplied ready for use. It should be added to the concrete mixes during the mixing process, at the same time as the water and aggregates are added. CONCRETE PROOF should not be added directly to the cement. Does not delay normal mixing time. It is always necessary to evaluate the performance of CONCRETE PROOF at tests at site and at batching plant and with the aggregates and sands that will be used. Such evaluations shall determine dosage rates against desired properties of concrete such as compressive strength; gains in early strength of concrete; shrinkage and other such characteristics of importance. As a guide for such trials, 500-800 ml of CONCRETE PROOF should be added per 100 kg of cement in order to evaluate workability of concrete in hot weather. Always consult BOTICA for such trials. Appropriate, reliable and exact dispensing equipment is available from BOTICA.

Disclaimer. All representations and recommendations set forth are given in good faith and the best of our knowledge. However due to varying conditions and applications the buyer shall conduct its own tests of this product before use. Under no circumstances will the manufacturer be liable for any loss or damages caused by incorrect usage. The sale of this product shall be on terms and conditions set forth on BOTICA's order acknowledgement

Factory : # 554, Street Troong Moan, Sangkat Stoeng Meanchey, Khan Mean Chey, Phnom Penh, Cambodia.

Office : # 249-251, Mao Tse Tong Blvd, Khan Chamkarmorn, Phnom Penh, Tel: 023 355 365, H/P: 016 55 99 09, Fax: 023 212 002, Email: info@botica.in

Effect of Overdosing

Overdosing will cause an increase in setting time. This is a serious condition that may lead to segregation of concrete, and thus a lowering of strength in top layers of floor-slabs and thus contributing towards inferior surface finishing. If this happens, do not disturb concrete after placement. Immediately stop further deliveries of ready-mixed concrete until dosage has been corrected. Contact BOTICA Technical Services immediately.

Characteristics

Appearance: brown liquid
Bulk density: 1.14 +/- 0.01 kg/l
pH value: 8.5-9.0
Freezing point: -2 °C
Flash-point: Non-flammable

Packaging

In drums of 210 kg.

Storage

BOTICA PROOF should preferably be or protected from frost. If the product does become frozen, it should be carefully mixed after thawing out to restore it to its normal state. Do not expose to direct sunlight

Precaution

Non-toxic. In case of contact with skin, wash with clean water. In case of eye contact, wash immediately with an abundance of clean water and contact eye doctor.

Disclaimer. All representations and recommendations set forth are given in good faith and the best of our knowledge. However due to varying conditions and applications the buyer shall conduct its own tests of this product before use. Under no circumstances will the manufacturer be liable for any loss or damages caused by incorrect usage. The sale of this product shall be on terms and conditions set forth on BOTICA's order acknowledgement

Factory : # 554, Street Troong Moan, Sangkat Stoeng Meanchey, Khan Mean Chey, Phnom Penh, Cambodia.

Office : # 249-251, Mao Tse Tong Blvd, Khan Chamkarmorn, Phnom Penh, Tel: 023 355 365, H/P: 016 55 99 09, Fax: 023 212 002, Email: info@botica.in